

## Physical Properties Bulletin

### Poly 15-Series Polyurethane Plastic Products

Product	15-3	15-3X	1511 & 1512	1512X
Mix Ratio (By Weight or Volume)	1A:1B	1A:1B	1A:1B	1A:1B
Part A Color	Opaque Tan <sup>1</sup>	Opaque Tan <sup>1</sup>	Clear Yellow	Clear Yellow
Part B Color	Opaque Tan <sup>1</sup>	Opaque Tan <sup>1</sup>	Translucent White <sup>1</sup>	Translucent White <sup>1</sup>
Mix Viscosity, cP	2,000	2,000	400	400
Pot Life, min	15	5	10 (1511) 22 (1512)	5
Maximum Exotherm, °F (°C)	125 (52)	160 (71)	251 (122)	251 (122)
Demold Time (hr)	12-16	1-12	1-16	½ - 4
Total Cure Time (days)	7	7	7	7
Linear Shrinkage	0.0006	0.0015	0.0044	0.0048
Specific Gravity	1.53	1.53	1.10	1.10
Shore D Hardness	80	80	71	71
Tensile Strength, psi (MPa)	3,509 (24.2)	3,890 (26.8)	6,712 (46.3) 7,882 (54.4)**	6,712 (46.3) 7,882 (54.4)**
Elastic Modulus, psi (MPa)	202,276 (1,395)	ND	118,352 (816.2) 112,073 (773.9)**	118,352 (816.2) 112,073 (773.9)**
Flexural Strength, 5% Strain, psi (MPa)	5,232 (36.1)***	ND	10,046 (69.3) 11,190 (77.2)**	10,046 (69.3) 11,190 (77.2)**
Flexural Modulus, psi (MPa)	479,648 (3,308)	ND	241,223 (1,663.4) 272,962 (1,882.5)**	241,223 (1,663.4) 272,962 (1,882.5)**
Heat Deflection Temperature, °F(°C)	ND	149 (65)	142 (61) 192 (89)**	142 (61) 192 (89)**
% Elongation	2.6	2.6	5.4 9.02**	5.4 9.02**

<sup>1</sup> Component requires stirring before use

\* Shrinkage, reported as inch/inch, is primarily caused by gelling while hot then cooling. Parts that cure with minimal temperature rise exhibit minimal shrinkage.

\*\* Post cured for 16 hours at 160°F (70°C)

\*\*\* Flexural Strength at Break

Convention: psi/145 = MPa (megapascals)

Disclaimer: The information in this bulletin and otherwise provided by Polytek is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained by the use thereof, or that any such use will not infringe any patent. The user shall determine the suitability of the product for the intended use and assumes all risk and liability whatsoever in connection therewith.